



Advanced Technical Products
Supply Co., Inc.
6186 Centre Park Drive
West Chester, OH 45069
USA

TECHNICAL DATA SHEET

ATP-134 Extrusion Glass

Description: A high temperature borosilicate glass with excellent lubricating and heat retention properties.

Properties:

Specific Gravity	2.55
Softening Point	1600 ^o F (921 ^o C)
Melting Point	1800 ^o F (1032 ^o C)
Hot Working Range	2100 - 2350 ^o F (1199-1337 ^o C)
Sieve Analysis	-30 +80 140 – 200 mesh

Composition: SiO₂
Na₂O
CaO
Al₂O₃
B₂O₃
MgO

Packaging:

Bags	50 lbs
Fiber Drums	200 lbs
Tote Bags	500 lbs

Uses: Pads

v 1.0 February 2014